

**DESCRIPTION**

URALASTIC<sup>TM</sup> 66 TOPCOAT Aliphatic Binder is a 100% solids, aliphatic isocyanate, single component, moisture cure high tensile strength UV stable binder for rubber EPDM granules. It is designed as a versatile binder for balconies, steps, pool decks and playground applications.

**FEATURES**

- ❖ Long Pot Life
- ❖ Non Yellowing
- ❖ Single Component
- ❖ Hydrolytic Stability
- ❖ Cold Temperature Flexibility
- ❖ Resilient
- ❖ Good Freeze-Thaw Flexibility
- ❖ Excellent Binding Characteristics

**TECHNICAL DATA**

Specific Gravity .....	1.03
Viscosity .....	3000 ± 500 cps
Total Solids by Weight, ASTM D-2369 .....	100%
Total Solids by Volume, ASTM D-2697 .....	100%
Tear Resistance, Die C, ASTM D-624 .....	450 ± 50 pli 78.8 ± 3.7 kN/m
Tensile Strength, ASTM D-412 .....	4000 ± 300 psi 27.6 ± 2.1 MPa
Ultimate Elongation, ASTM D-412 .....	550 ± 50 %

Note: Above physicals are from lab drawn films.

**COLOR**

Clear

**PACKAGING**

5 gallon pail  
55 gallon drum, net fill 50 gallons 250 gallon tote

**STORAGE**

URALASTIC<sup>TM</sup> 66 is supplied in pails, drums or totes. Once a container has been opened, care should be taken to exclude moisture. Best temperature for storage is 75-95° F (25-35°C). If stored at higher temperatures, or if moisture is not excluded, shelf-life is reduced.

**WARNING**

This product contains Isocyanates.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local GoRubber Coatings representative or visit our website for current technical data and instructions.

**LIMITED WARRANTY**

GoRubber Coatings warrants its products to be free of manufacturing defects and that they will meet GoRubber Coatings current published physical properties. GoRubber Coatings warrants that its products, when properly installed by a state licensed waterproofing contractor according to GoRubber Coatings guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of 12 months. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by GoRubber Coatings of any nature whatsoever expressed or implied, luding any warranty of merchantability or fitness for a particular purpose in connection with this product. GoRubber Coatings shall not be liable for damages of any sort, luding remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. GoRubber Coatings shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. GoRubber Coatings reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

**DISCLAIMER**

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and GoRubber Coatings makes no claim that these tests or any other tests, accurately represent all environments.