

Technical Data Sheet GO602

Waterproof Rubber Sealant Paste

PRODUCT DESCRIPTION

GORUBBER™ 602 is a two component, elastomeric aliphatic polyurethane surface clear sealer for interior and exterior use. It has good gloss and color retention. **GORUBBER™ 602** can be used over rubber surface due to its high flexibility.

PRODUCT FEATURES

- Excellent flexibility
- High Quality U.V. resistance
- High viscosity

- Excellent adhesion to rubber and PVC
- Excellent abrasion resistance
- Good weathering
- **TYPICAL USES**

- Water park
- Playground

- Splash pads
- Water basins

TECHNICAL DATA

Colors available:	Clear	Drying times: (23°C 77°F)	
Sollids by volume:	78 % +/- 2 %	Dust Free:	4 - 6 hours
Solids by Weight:	83 % +/- 2 %	To recoat:	4 hours
Theoretical Coverage of 1 mil:	1248 ft² / U.S gallon	Hard:	24 hours
D.F.T. at 25 microns:	114 m² / 3.78 litres		
Recommended coverage:	40 - 80 ft²/gls	Pot Life:	1 hour @ 22°C (72°F)
Specific gravity	1.05 - 1.15 kg/lt	Reduction solvent:	GO-500 Regular GO-502 Slow
Flash Point:	26°C (78.8°F)	Dilution:	10 - 15 % by volume
V.O.C.:	190 grams/liter 1.58 lbs / US gal.	Catalyst:	GO602C
		Ratio:	3:1
		Packaging:	2.84 liter (1 U.S gallon)

Keep in cool and dry area ***revised on August 24, 2020**



GoRubber Coatings Laval, QC Canada H7L 5A1 www.gorubber.ca 11.34 liter (U.S gallon)



APPLICATION GUIDE

SURFACE PREPARATION

Prior to surface preparation, remove all grease, oil, salts and moisture. Fix all crack or crevice prior to sealing. After surface preparation, vacuum or remove dust and ensure the surface remains clean and dry before applying.

MIXING AND THINNING

The entire contents of container must be mixed well before application. Thinning up to 15 % can be done if required.

NOTE: Drying times will vary depending on solvent combination used.

APPLICATION PROCESS

			* RECOATING TIME		
Substrate temperature	Dust free	Hard	Minimum	Maximum	Normal
25°C (72°F)	4 - 6 hours	24 hours	4 hours	48 hours	12 hours

Apply by trowel or squeegee

PRODUCT LIMITATIONS

• Shelf life: 12 months

See the material safety data sheet and product label for complete safety and precaution requirements. DISCLAIMER:

"The following is made in lieu of all warranties, expressed or implied: Manufacturer's obligation shall be to replace such quantity of the product proven to be defective. The manufacturer shall not be liable for any injury, loss or damage, direct or incidental or consequential, arising out of the use of or the inability to use the product. Before using, the user shall determine the suitability of the product for the intended use and the user assumes all risk and liability whatsoever in connection therewith. All values shown are approximations. Values indicated are for guide purposes only, as actual values can change due to application conditions, application methods, environmental conditions etc. The information contained herein is subject to change without notice. Consult your representative for a current data sheet. The foregoing may not be altered except by an agreement signed by the officers of the manufacturer."

Chemical resistance information is currently being updated according to ASTM standards Please contact your local representative for an update.



GoRubber Coatings Laval, QC Canada H7L 5A1 www.gorubber.ca